# nomeo flooring.

Issue Date: 01/10/2023, rev. 1

# **PRODUCT TECHNICAL DATA SHEET**

# **ONEisol PU25**

Single-component, polyurethane, thixotropic sealant

# **Product Description**

Single-component, polyurethane, thixotropic sealant, moisture curing, for bonding and sealing

# **Characteristics**

- ✓ Elastic sealant capable of movement
- ✓ Adhesion to different surfaces
  ✓ Easy application at temperatures of +5 °C to +40 °C
- ✓ Very good resistance to ageing (UV and humidity)
- ✓ High mechanical strength
- ✓ Operating temperature -40 °C to +90 °C
- ✓ Can be painted over
- ✓ Thixotropic consistency does not flow

# **Application Suitability**

The product is suitable for:

- ✓ Sealing and bonding of expansion joints
- ✓ Bonding in industrial applications
- ✓ Adhesion to most substrates:
  - ✓ Concrete
  - $\checkmark$ Glass
  - $\checkmark$ Wood
  - Anodized aluminium
  - ✓ Tiles, etc.

# **Technical Specifications**

Dry to touch	(23°C, 50% RH)	120–240 min	
Cure speed	(23°C, 50% RH)	approx. 2–3 mm/day	
Density	(21 °C)	$1.23 \text{ kg/l} \pm 5\%$	EN ISO 2811-1
Elongation at break		550%	ISO 8339
Temperature resistance		-40 to 90 °C	
Movement capability		25%	ISO 4624
Modulus at 100% elongation		0.32 N/mm <sup>2</sup>	ISO 8339
Hardness (Shore A)	(23 °C)	approx. 25	DIN 53 505
Tensile strength		0.82 N/mm <sup>2</sup>	ISO 8339

# nomeo flooring.

Issue Date: 01/10/2023, rev. 1

# Application

# Substrate Preparation

Joint preparation: the surfaces to be bonded must be clean, dry and free of dust, oil, grease, old sealant and any contaminants that may affect adhesion. Degrease with solvent and blow off the dust with compressed air.

**Temperature of the substrate, environment and material:** +5 °C min / +40 °C max

# **Application Instructions**

- ✓ Priming: only in case of highly porous concrete; use ONEbasic
- ✓ Apply sealant, maximum joint width 40 mm
- ✓ Smooth the surface of the uncured sealant with a spatula
- ✓ Clean excess uncured sealant with thinner (e.g. xylene)
- ✓ Cured sealant can only be cleaned mechanically

# **Tool Cleaning and Environmental Protection**

Clean tools immediately after application with acetone, xylene or thinner ONEisol-S. The cured material can only be removed mechanically. Avoid contamination of the environment.

# **Packaging and Storage**

Packaging:	cartridge 310 ml (25 pcs), sausage 600 ml (15 pcs)
Colours:	white, grey
Storage: Shelf life:	+5 °C to +30 °C 12 months in original, unopened and undamaged packaging from date of manufacture

# **Safety Regulations and Protective Measures**

Safety instructions and applicable OSH regulations of the relevant authorities must be observed when handling. Use protective clothing, goggles and gloves during application. Detailed information on hygiene, occupational safety and environmental protection is provided in the Safety Data Sheet.

#### **Legal Notice**

The information, especially the handling and application instructions for our products, is based on our knowledge of the development and application of chemical products and our many years of application experience under standardized conditions and proper storage and use. In view of the different preparation conditions, external influences of varying nature and the characteristics of the substrates, following the above information or other written or oral recommendations may not always guarantee a satisfactory work result. The client/contractor must test the products to ensure that they are suitable for the intended application.